

AMENDMENTS TO THE SPECIFICATION:

Please replace the paragraph beginning at page 15, line 10, with the following amended paragraph:

<38> The method for producing an organometallic complex structure according to any one of the <35> to <38> <37>, wherein the amount of organic polymer to be mixed at the mixing satisfies: (mole of the organic polymer/mole of the metal atom) ≥ 20 . In the method for producing an organometallic complex structure, when the molar ratio of the organic polymer and the metal ion is set to 20 or more, a uniform nanowire crystal of organometallic complex structure with a certain diameter (100 nm to 400 nm) can be obtained efficiently.